



# 厦门市三磊包装材料有限公司

## XIAMEN THREESTONE PACKING MATERIAL CO.,LTD

工厂：中国福建省厦门市同安工业集中区思明园117号  
 Factory: 117 Siming Yuan, Tong'an Muster Industrial Zone  
 Xiamen, Fujian, China  
 Tel: (86-592) 5219500 5219600  
 Fax: (86-592) 5217833  
 Http://www.threestone.com.cn

国际业务部地址：中国福建省厦门市湖里区创业园诚业楼404室  
 ADD: Unit 404, Chengye Building, Pioneering Park, Xiamen, 361015, Fujian, China  
 Tel: (86-592) 5501369  
 Fax: (86-592) 5501269  
 E-mail: sales@3Lei.com  
 Http://www.3Lei.com



### Technical Date Sheet

Product: nylon film 25um

Properties		Test Method	Units	Target Value	Typical Value
Density		N/A	g/cm3	1.15	1.15
Thickness		Q/XMSL 005-2016	Mu	±6%	2.6
Seal Strength		Q/XMSL 005-2016	N/mm	≥7	16
Tensile Strength	MD	Q/XMSL 005-2016	MPa	≥25	36
	TD	Q/XMSL 005-2016		≥25	28
Elongation	MD	Q/XMSL 005-2016	%	≥160	220
	TD	Q/XMSL 005-2016		≥100	201
Heat Shrinkage (200℃, 45min)	MD	Q/XMSL 005-2016	%	≤3.0	1.50%
	TD	Q/XMSL 005-2016		≤3.0	1.30%